

UBE NYLON 1013B

Technical Product Information

UBE NYLON 1013B is a low viscosity, unmodified Polyamide 6 for general application. This material has following features:

- Excellent mechanical properties
- Good processability

Basic Properties ⁽¹⁾		Method	Unit	Value
Polymer		-	-	PA6
Colour		-	-	Natural
Density		ISO 1183-3	g/cm ³	1,14
Melting Point		ISO 11357	°C	215 - 225
Relative Viscosity (96% H ₂ SO ₄)		JIS K6810	-	2,45

Mechanical Properties ⁽²⁾		Method	Unit	Value
Tensile stress at yield		ISO 527-1,2	MPa	80
Tensile strain at break			%	30
Tensile modulus			MPa	2900
Flexural strength		ISO 178	MPa	110
Flexural modulus			MPa	2700
Charpy impact strength (notched) ⁽³⁾	23°C	ISO 179/1eA	kJ/m ²	6 C

Thermal Properties ⁽²⁾		Method	Unit	Value
Temp. of deflection under load	0,45 MPa	ISO 75-2	°C	155
	1,80 MPa		°C	60
Coefficient of linear expansion		ISO 11359-2	x 10 ⁻⁴ /K	0,8

Others ⁽⁴⁾		Method	Unit	Value
Molding shrinkage	MD	UBE Method	%	1,4
	TD		%	1,5

Note: All tests carried dry as mould

(1) Measured on pellets

(2) Measured on injection-moulded specimens, based on ISO type

(3) P=partial break, C=complete break

(4) Sample dimension is 30×100×3mm

Processing conditions

	Cylinder					Die
	Hopper	Zone 1	Zone 2	Zone 3	Zone 4	
Temperature (°C)	40 - 120	210-230	230 - 250	240 - 260	240 - 260	240 - 260

Drying conditions

UBE NYLON is supplied dry (moisture content < 0,1%) and packed in high barrier films. However, as polyamide is a hygroscopic material, the user should take a special care of the possible moisture absorption once the bag or liner box has been opened. In case of moisture absorption, the material should be dried with dehumidified air at 80°C for more than 4 hours.

Storage

Well-sealed packages could be stored in cool and dry conditions over long periods of time. Protect the packages from heat and direct sunlight to prevent possible damages.

Health & environmental data

Please refer to the corresponding **UBE NYLON** grade Safety Data Sheet (SDS).

IMPORTANT NOTICE:

The contents of here written materials were prepared based on materials, information and data available at the present moment. They may be revised because of new knowledge, information and data without notification. The data described herein are averaged values obtained by specific measurement. They are not guaranteed figures. UBE does not warrant or guarantee the quality or safety of your finished products, including but not limited to implied warranties of merchantability, fitness for a particular purpose and non-infringement of third-party rights or arising from a course of dealing, usage or trade practice even if UBE's products and data herein or any other information proposed by UBE are used to manufacture the finished products. Determination of suitability, merchantability or fitness for a particular purpose of your finished products shall be on your responsibility. UBE has no liability or legal responsibility for any issues or problems in relation to standards, regulations, laws, intellectual property rights - especially patent rights, etc. derived from any applications of UBE products for your finished products. So it should be fully researched and studied by yourself. UBE highly recommends reading Safety Data Sheet "SDS" before using UBE Products to ensure your safety. "UBE NYLON" and "UBESTA" is registered trademark in Japan and other countries.