

## UBE NYLON 5024FDN1

### Technical Product Information: AIR-BLOWN – PA monolayer film properties

UBE NYLON 5024FDN1 is a nucleated, medium viscosity Polyamide 6/6.6 copolymer. The grade is especially suitable as outer layer for a wide range of applications where high optical properties are requested. This material has the following features:

- Excellent processability
- Excellent mechanical properties
- Excellent puncture resistance
- Excellent optical properties

Basic Properties <sup>(1)</sup>	Method	Unit	Value
<b>Polymer</b>	-	-	PA6/6.6
<b>Melting Point</b>	ISO 11357	°C	192
<b>Relative Viscosity (96% H<sub>2</sub>SO<sub>4</sub>)</b>	JIS K6810	-	3,40
<b>Density</b>	DIN 53479	g/cm <sup>3</sup>	1,14

Mechanical Properties <sup>(2)</sup>	Method	Unit	Value
<b>Tensile strength at yield</b>	ISO 527-3	MPa	26 - 30
<b>Tensile strength at break</b>		MPa	100 - 120
<b>Tensile elongation at break</b>		%	440 - 460
<b>Tensile modulus</b>		MPa	550 - 650
<b>Tear resistance</b>	ASTM D 1922	N	1,6 - 1,8
<b>Puncture energy</b>	JAS P-1019	mJ	30 - 32
<b>Puncture deformation</b>		mm	8,0 - 9,0
<b>Spencer impact resistance</b>	ASTM D 3420	mJ	850 - 950
<b>Flex crack (23°C, 1000 cycles / 5°C, 100 cycles)</b>	Mil B-131C	Holes/0,04m <sup>2</sup>	< 20 / < 5

Optical Properties <sup>(2)</sup>	Method	Unit	Value
<b>Haze</b>	ASTM D 1003	%	1 - 3
<b>Gloss</b>	ASTM D 523	%	130 - 150

Gas Barrier <sup>(2)</sup>	Method	Unit	Value
<b>Oxygen (T=23°C, RH=0%)</b>	ASTM D 3985	ml/m <sup>2</sup> .day	23 - 25
<b>Water Vapour (T=40°C, RH=90%)</b>	JIS Z-0208	g/m <sup>2</sup> .day	150 - 170

Slip Properties <sup>(2)</sup>	Method	Unit	Value
Coefficient of friction (static)	ASTM D 1894	-	0,40 - 0,44
Coefficient of friction (dynamic)		-	0,40 - 0,44

Thermoforming Properties <sup>(2)</sup>	Method	Unit	Value
Max. Thermoforming depth	UBE METHOD	mm	75 - 85

Regulation	Method	Unit	Value
FDA / EC	-	-	I&D / I&D

I: Approved for indirect food contact D: Approved for direct food contact

(1) Measured on base resin

(2) All tests carried out with a 5 layers airblown line, Die diameter = 90 mm · Die gap=1,4 mm

Structure: PE (outer) / PE / PA (medium) / PE / PE (inner), PA layer delaminated for the tests

Layer thickness distribution: PE = 50 µm, PA = 50 µm, PE = 50 µm (Total film thickness = 150 µm) · Cooling conditions: Chiller temp. = 13 °C · Take off rolls = 35 °C

Film orientation: Blow-up ratio = 2,1 · Take-off speed = 6m min-1 · Sample conditioning and testing conditions: T = 23°C, RH =50%

## Processing conditions

	Extruder					Adaptor	Die
	Hopper	Zone 1	Zone 2	Zone 3	Zone 4		
Temperature (°C)	40 - 120	180 - 200	220 - 240	230 - 250	225 - 245	230 - 250	230 - 250

## Drying conditions

UBE NYLON is supplied dry (moisture content < 0,1%) and packed in high barrier films. However, as polyamide is a hygroscopic material, the user should take a special care of the possible moisture absorption once the bag or liner box has been opened. In case of moisture absorption, the material should be dried with dehumidified air at 80°C for more than 4 hours.

## Storage

Well-sealed packages could be stored in cool and dry conditions over long periods of time. Protect the packages from heat and direct sunlight to prevent possible damages.

## Health & environmental data

Please refer to the corresponding **UBE NYLON** grade SDS.

### IMPORTANT NOTICE:

The contents of here written materials were prepared based on materials, information and data available at the present moment. They may be revised because of new knowledge, information and data without notification. The data described herein are averaged values obtained by specific measurement. They are not guaranteed figures. UBE does not warrant or guarantee the quality or safety of your finished products, including but not limited to implied warranties of merchantability, fitness for a particular purpose and non infringement of third party rights or arising from a course of dealing, usage or trade practice even if UBE's products and data herein or any other information proposed by UBE are used to manufacture the finished products. Determination of suitability, merchantability or fitness for a particular purpose of your finished products shall be on your responsibility. UBE has no liability or legal responsibility for any issues or problems in relation to standards, regulations, laws, intellectual property rights - especially patent rights, etc. derived from any applications of UBE products for your finished products. So it should be fully researched and studied by yourself. UBE highly recommends reading Safety Data Sheet "SDS" before using UBE Products to ensure your safety. "UBE NYLON" and "UBESTA" is registered trademark in Japan and other countries.