UBE CORPORATION EUROPE S.A.U.
Polígono El Serrallo s/n
12100 Castellón, Spain
Tel: +34 964 73 80 00
Fax: +34 964 73 81 80
www.ube.es

UBE NYLON 7034T

Technical Product Information: Monofilament properties

UBE NYLON 7034TX is a high viscosity modified Polyamide 6/12 copolymer for monofilament application, suitable for small and large diameter size. The material allows high drawing ratios resulting in superior line strength. This material has the following features:

- Excellent transparency
- Superior line strength and tenacity
- Outstanding processability

Basic Properties [1]	Method	Unit	Value
Polymer	-	-	PA6/12
Melting Point	ISO 11357	°C	201
Relative Viscosity (96% H_2SO_4)	JIS K6810	-	3,86
Density	DIN 53479	g/cm³	1,14

Mechanical Properties [2]		Unit	Value					
Mechanical properties of monofilament d = 0,3mm								
Draw ratio (G3/G1)			**4,5**	**5,0**	**5,5**	**6,0**	**6,5**	**7,0**
Line	Strength	g/d	5,0 - 6,0	6,0 - 7,0	7,0 - 8,0	8,5 - 9,5	9,0 - 10,0	9,0 - 10,0
	Tenacity	kg	3,5 - 4,5	4,0 - 5,0	4,5 - 5,5	5,5 - 6,5	6,0 - 7,0	6,0 - 7,0
	Elongation	%	65 - 75	45 - 55	35 - 45	30 - 40	20 - 30	15 - 25
Tensile modulus		g/d	10 - 14	12 - 16	14 - 18	16 - 20	18 - 22	18 - 22
Knot	Strength	g/d	4,5 - 5,5	5,0 - 6,0	5,5 - 6,5	7,0 - 8,0	7,0 - 8,0	6,5 - 7,5
	Tenacity	kg	3,0 - 4,0	3,5 - 4,5	3,5 - 4,5	4,5 - 5,5	4,5 - 5,5	4,0 - 5,0
	Elongation	%	55 - 65	35 - 45	25 - 35	20 - 30	15 - 25	15 - 25
Mechanical properties of monofilament d = 2,0mm								
Draw ratio (G3/G1)			**4,5**	**5,0**	**5,5**	**6,0**	**6,5**	**7,0**
Line	Strength	g/d	3,5 - 4,5	4,5 - 5,5	5,5 - 6,5	6,0 - 7,0	5,5 - 6,5	
	Tenacity	kg	120 - 140	150 - 170	190 - 210	200 - 220	190 - 210	
	Elongation	%	35 - 45	30 - 40	25 - 35	20 - 30	15 - 25	
Tensile modulus		g/d	18 - 22	18 - 22	20 - 24	22 - 26	22 - 26	
Knot	Strength	g/d	2,0 - 3,0	2,5 - 3,5	2,5 - 3,5	2,5 - 3,5	2,5 - 3,5	
	Tenacity	kg	70 - 90	80 - 100	90 - 110	90 - 110	90 - 110	
	Elongation	%	35 - 45	25 - 35	20 - 30	20 - 30	20 - 30	

UBE CORPORATION EUROPE S.A.U.
Polígono El Serrallo s/n
12100 Castellón, Spain
Tel: +34 964 73 80 00
Fax: +34 964 73 81 80
www.ube.es

(1) Measured on base resin
(2) All tests carried out on monofilaments produced with a 35mm screw
Extrusion temperatures between 240-275°C
Quench bath temperature: 15°C
Drawing temperature: 1st = 95°C (hot water); 2nd = 180°C; Heat set = 180°C
Relaxation ratio (G4/G3) = 1; Line speed (G4) = 28 m·min^{-1}
Sample conditioning and testing conditions: T = 23°C, RH =50%

Processing conditions

	Extruder					Adaptor	Die
	Hopper	Zone 1	Zone 2	Zone 3	Zone 4		
Temperature (°C)	40 - 120	180 - 200	200 - 220	210 - 230	220 - 240	230 - 250	230 - 250

	Quenching bath	1st drawing	2nd drawing	Heat setting
Temperature (°C)	8 - 15	90 - 100	170 - 190	170 - 190

Drying conditions

UBE NYLON is supplied dry (moisture content < 0,1%) and packed in high barrier films. However, as polyamide is a hygroscopic material, the user should take a special care of the possible moisture absorption once the bag or liner box has been opened. In case of moisture absorption, the material should be dried with dehumidified air at 80°C for more than 4 hours.

Storage

Well-sealed packages could be stored in cool and dry conditions over long periods of time. Protect the packages from heat and direct sunlight to prevent possible damages.

Health & environmental data

Please refer to the corresponding **UBE NYLON** grade SDS.

IMPORTANT NOTICE:
The contents of here written materials were prepared based on materials, information and data available at the present moment. They may be revised because of new knowledge, information and data without notification. The data described herein are averaged values obtained by specific measurement. They are not guaranteed figures. UBE does not warrant or guarantee the quality or safety of your finished products, including but not limited to implied warranties of merchantability, fitness for a particular purpose and non infringement of third party rights or arising from a course of dealing, usage or trade practice even if UBE's products and data herein or any other information proposed by UBE are used to manufacture the finished products. Determination of suitability, merchantability or fitness for a particular purpose of your finished products shall be on your responsibility. UBE has no liability or legal responsibility for any issues or problems in relation to standards, regulations, laws, intellectual property rights - especially patent rights, etc. derived from any applications of UBE products for your finished products.
So it should be fully researched and studied by yourself. UBE highly recommends reading Safety Data Sheet "SDS" before using UBE Products to ensure your safety. "UBE NYLON" and "UBESTA" is registered trademark in Japan and other countries.